

# ULTRA Outre

Beyond Your Expectations

## Technical Data Sheet DS100

*100 g/m<sup>2</sup> Coated 2-Side Matte Paper*

PHYSICAL PROPERTIES	RESULT	UNIT	STANDARD
BASIS WEIGHT	113 ± 8	g/m <sup>2</sup>	ISO 536
PAPER THICKNESS	142 ± 10	um	ISO 534
OPACITY	> 92	%	ISO 2471
STIFFNESS (MD)	13 ± 1	mN	ISO 2493
STIFFNESS (CD)	6 ± 1	mN	ISO 2493
SMOOTHNESS	32 ± 10	sec	ISO 5627
CIE WHITENESS	155 ± 10	%	ISO 11475
SHADE	L*	96 ± 1	ISO 5631-2
	a*	4 ± 1	ISO 5631-2
	b*	-14.5 ± 1	ISO 5631-2
LAMINATION	COLD: YES	HOT: YES	
PROCESSING	Best printing results occur in a standard climate of 23°C and 50% relative humidity. For problem-free running, always store the printing medium in the original packaging and protect it from direct sunlight and moisture.		
NOTE: For use in Epson, Canon, and HP aqueous printers with dye and pigmented inks.	All above information shall only be used as a guide; Buyers shall independently test and determine the products suitability. The mentioned data are an average of test results and should not be used for the purpose of lawsuit or warranty. Above specifications may change without notice.		



[www.myoutre.com](http://www.myoutre.com)

#1 Network  
309 Professional Park Avenue  
Effingham, IL 62401  
Phone: 217-536-5737  
Fax: 217-536-5141

10/23/09