

# ULTRA Outre

Beyond Your Expectations

## Technical Data Sheet DS168S

*168 g/m<sup>2</sup> Coated 2-Side Semi-Gloss Proofing Paper*

PHYSICAL PROPERTIES	RESULT	UNIT	STANDARD
BASIS WEIGHT	165 ± 10	g/m <sup>2</sup>	ISO 536
CALIPER	200 ± 12	um	ISO 534
OPACITY	95 ± 5	%	ISO 2471
STIFFNESS BEKK, FRONT SIDE	120 ± 50	%	ISO 5627
STIFFNESS BEKK, BACK SIDE	120 ± 50	%	ISO 5627
GLOSS 75 DEGREE, FRONT	53 ± 7	%	ISO 8254
GL;OSS 75 DEGREE, BACK	53 ± 7	%	ISO 8254
ISO BRIGHTNESS, FRONT	90 ± 7	%	ISO 2470
ISO BRIGHTNESS, BACK	90 ± 7	%	ISO 2470
PROCESSING	Best printing results occur in a standard climate of 23°C and 50% relative humidity. For problem-free running, always store the printing medium in the original packaging and protect it from direct sunlight and moisture.		
NOTE: For use in Epson, Canon, and HP aqueous printers with dye and pigmented inks.	All above information shall only be used as a guide; Buyers shall independently test and determine the products suitability. The mentioned data are an average of test results and should not be used for the purpose of lawsuit or warranty. Above specifications may change without notice.		



[www.myoutre.com](http://www.myoutre.com)

#1 Network  
309 Professional Park Avenue  
Effingham, IL 62401  
Phone: 217-536-5737  
Fax: 217-536-5141

10/26/09