

BACKLIT15M

15oz BACKLIT BANNER

Fire Certificate



REPORT # : H214-08-16839-02
 SAMPLE RECEIVED DATE : 09-04-2008
 TEST STARTED DATE : 09-04-2008
 REPORT ISSUED DATE : 09-09-2008

TEST CONDUCTED: **FLAMMABILITY { NFPA 701 TEST METHOD 1 (2004)}**

TEST RESULT:

SAMPLE NUMBER	WEIGHT (g)		WEIGHT LOSS (%)	AFTER FLAME TIME (s)	DRIP BURNS (s)
	ORIGINAL	AFTER			
1	33.4	28.3	15.3	0.0	0.0
2	33.3	28.1	15.6	0.0	0.0
3	33.5	28.8	14.0	0.0	0.0
4	33.3	28.8	13.5	0.0	0.0
5	33.4	28.6	14.4	0.0	0.0
6	33.4	28.1	15.9	0.0	0.0
7	33.3	27.9	16.2	0.0	0.0
8	33.4	28.1	15.9	0.0	0.0
9	33.5	27.9	16.7	0.0	0.0
10	33.3	28.4	14.7	0.0	0.0
AVG	33.4	28.3	15.2	0.0	0.0

Note - Conclusion: Based upon the results of the test report, the submitted sample meets the performance requirement as stated in NFPA 701 TEST METHOD 1 (2004).

PERFORMANCE CRITERIA FOR TEST 1:

DRIP BURN(S)	WEIGHT LOSS (%)	NO INDIVIDUAL SPECIMEN'S WEIGHT LOSS EXCEED THE MEAN VALUE PLUS 3 STANDARD DEVIATION 18.3 (STANDARD DEVIATION = 1.03)
AVG: LESS THAN 2	AVG: LESS THAN 40	

TEST WAS CONDUCTED ONLY IN THE ORIGINAL STATE BY THE CLIENTS REQUEST.