

Outre^{ULTRA}

Beyond Your Expectations

Technical Data Sheet

PH200SGRA

8 mil Microporous RC, GRACoL

PHYSICAL PROPERTIES	RESULT	UNIT	STANDARD
BASIS WEIGHT	200 ± 10	g/m ²	ISO 536
CALIPER	202 ± 12	um	ISO 534
GLOSS 75 DEGREE	51.0 ± 5.0	%	ISO 8254
ISO BRIGHTNESS	89.0 ± 2.0	%	ISO 2470
OPACITY	94.0 ± 4.0	%	ISO 2471
WHITENESS L*	95.5 ± 1.5		
a*	0.0 ± 0.8		ISO 5631
b*	-1.0 ± 0.8		
STIFFNESS (MD)	1.00 ± 0.8	mN.m	ISO 2493
STIFFNESS (CD)	0.55 ± 0.5	mN.m	ISO 2493
<p>NOTE: For use in Epson, Canon, and HP aqueous printers with dye and pigmented inks.</p> <p>All above information shall only be used as a guide; Buyers shall independently test and determine the products suitability. The mentioned data are an average of test results and should not be used for the purpose of lawsuit or warranty. Above specifications may change without notice.</p>			



www.myoutre.com

#1 Network
309 Professional Park Avenue
Effingham, IL 62401
Phone: 217-536-5737
Fax: 217-536-5141

4/20/10