

Outre^{ULTRA}

Beyond Your Expectations

Technical Data Sheet PH250S

10 mil Microporous Satin Photobase

PHYSICAL PROPERTIES	RESULT	UNIT	STANDARD
BASIS WEIGHT	255 ± 10	g/m ²	ISO 536
THICKNESS	265 ± 12	um	JIS P-8118
GLOSS 75 DEGREE	50.0 ± 5.0	%	ISO 8254
ISO BRIGHTNESS	91.0 ± 4.0	%	ISO 2470
OPACITY	96.0 ± 4.0	%	ISO 2471
STIFFNESS (MD)	2.3 ± 0.8	mN.m	ISO 2493
STIFFNESS (CD)	1.3 ± 0.5	mN.m	ISO 2493
NOTE: For use in Epson, Canon, and HP aqueous printers with dye and pigmented inks.		All above information shall only be used as a guide; Buyers shall independently test and determine the products suitability. The mentioned data are an average of test results and should not be used for the purpose of lawsuit or warranty. Above specifications may change without notice.	



www.myoutre.com

#1 Network
309 Professional Park Avenue
Effingham, IL 62401
Phone: 217-536-5737
Fax: 217-536-5141

6/21/11