

ULTRA Outre

Beyond Your Expectations

Technical Data Sheet

PH255SW05

10 mil Microporous RC, SWOP #5

| PHYSICAL PROPERTIES | RESULT | UNIT | STANDARD |
|---|---|------------------|----------------------|
| BASIS WEIGHT | 255 ± 10 | g/m ² | ISO 536 |
| CALIPER | 270 ± 12 | um | ISO 534 |
| GLOSS 75 DEGREE | 49.0 ± 5.0 | % | ISO 8254 |
| ISO BRIGHTNESS | 69.0 ± 3.0 | % | ISO 2470 |
| OPACITY | 98.0 ± 4.0 | % | ISO 2471 |
| WHITENESS L* | 90.0 ± 1.5 | | X-RITE i-1 PRO D50/2 |
| a* | 0.0 ± 0.8 | | |
| b* | 4.0 ± 0.8 | | |
| STIFFNESS (MD) | 2.30 ± 0.8 | mN.m | ISO 2493 |
| STIFFNESS (CD) | 1.40 ± 0.5 | mN.m | ISO 2493 |
| NOTE: For use in Epson, Canon, and HP aqueous printers with dye and pigmented inks. | All above information shall only be used as a guide; Buyers shall independently test and determine the products suitability. The mentioned data are an average of test results and should not be used for the purpose of lawsuit or warranty. Above specifications may change without notice. | | |



www.myoutre.com

#1 Network
309 Professional Park Avenue
Effingham, IL 62401
Phone: 217-536-5737
Fax: 217-536-5141

01/10/12