

# ULTRA Outre

Beyond Your Expectations

## Technical Data Sheet S120

*120 g/m<sup>2</sup> Coated 1-Side Matte Paper*

PHYSICAL PROPERTIES	RESULT	UNIT	STANDARD
BASIS WEIGHT	118 ± 7	g/m <sup>2</sup>	ISO 536
PAPER THICKNESS	150 ± 9	um	ISO 534
OPACITY	93 ± 3	%	ISO 2471
STIFFNESS (MD)	11 ± 6	mN	ISO 2493
STIFFNESS (CD)	6 ± 3	mN	ISO 2493
SMOOTHNESS	49 ± 12	S (Bekk)	ISO 5627
CIE WHITENESS	155 ± 5	%	ISO 11475
SHADE	L*	97 ± 2	
	a*	3.7 ± 1	
	b*	-14.5 ± 2	
LAMINATION	COLD: YES	HOT: YES	
PH LEVEL	7.0 Neutral (acid-free)		
PROCESSING	Best printing results occur in a standard climate of 23°C and 50% relative humidity. For problem-free running, always store the printing medium in the original packaging and protect it from direct sunlight and moisture.		
NOTE:	All above information shall only be used as a guide; Buyers shall independently test and determine the products suitability. The mentioned data are an average of test results and should not be used for the purpose of lawsuit or warranty. Above specifications may change without notice.		
For use in Epson, Canon, and HP aqueous printers with dye and pigmented inks.			



[www.myoutre.com](http://www.myoutre.com)

#1 Network  
309 Professional Park Avenue  
Effingham, IL 62401  
Phone: 217-536-5737  
Fax: 217-536-5141

11/09/11